



# PAMPA ENTERPRISES

No: 18, Paramavyoma, 4th Cross, Behind M.H. Kalyana Mantapa, Hosakerehalli, BSK 3rd Stage, Bangalore - 560085

Phone: +91 80 26724918 , Fax: +91 80 30723657, Mobile: 9845508582,

E-mail: pampa@pampaco.in, pampa@vsnl.com, pamp@dataone.in, Website: www.pampa.co.in

---

## Technical data Sheet

### FERRO ALLOYS

1. Ferro Silicon	Si-70-75%, S-0.02%, P-0.049%, Al-0.62%, C-0.09%
2. Ferro Silicon	Si-75-80%, S-0.02%, P-0.049%, Al-0.62%, C-0.09%
3. Ferro Phosphorus	P-26.3%, C-1.0%
4. Calcium Silicide	Si-65%, Ca-30%, C-1%, Su-0.05%, Al-1%, P-0.05%
5. Silicon Manganese	Mn-60-65%, Si-15-18%, C-1.5-2%, S-0.05%, P-0.03%
6. Silicon Manganese	M/C Mn-58%, Si-22%, C-1%
7. Ferro Manganese	H/C Mn-70-75%, C-7%, Si-1.2%, S-0.03%, P-0.34%
8. Ferro Manganese	L/C Mn-70-75%, C-0.15% max., Si-1.2%, S-0.03%, P-0.34%
9. Ferro Molybdenum	Mo-60%, Si-1.4%, C-0.06%, S-0.03%, P-0.03%
10.Ferro Chrome	H/C (60% Prorata) Cr-60-65%, C-7.1%, S-0.046%, P-0.048%
11.Ferro Chrome	L/C (65% Prorata) Cr-65.2% Min, C-0.1%, S-0.04%, P-0.028%
12.Ferro Vanadium	V-50-55%, Si-1.5%, C-0.1%, S-0.05%, Al-15%, P-0.05%
13.Ferro Titanium	Ti-25-30%/30-35%) Al-1%, C-0.1%, Si-3%, s-0.060%, P-0.10%
14.Ferro Niobium	Nb-65%, Si-0.18%, C-0.10%, P-0.089%
15.Ferro Silicon Magnesium	Mn-8-10%, Si-45-50%, Al-1.25%, C-0.82% Rare Earth-1.5-2%, Mish Metal-0.1%
16.Ferro Boron	B-30%, C-2%, S-4%, Al-0.5%
17.Ferro Tungsten	W-85%, C-0.06%, Si-1.0%, P-0.06%, S-0.050%
18.Ferro Sulphur (Ferrous sulphide)	FeS- 80~85%, S-25~32%, C-0.3%, P-0.035%, S-0.03%
19.Ferro Aluminum	Fe: 47~52%, Al: 47~52%, Si:0, 20%, C:0, 10%, Mn:0, 40%, P:0, 03%, S:0, 03%